




# REVIVE

TECHNICAL SPECIFICATION



# Revive


Terrazzo Effect Porcelain Tiles in a blend of neutral colours.




Exterior



Heavy Footfall



Pool Edging



Stairs

## Sizes

80 X 80  
60 X 60  
30 X 60  
15 X 60  
5 X 5  
30 X 30  
30 X 60  
7 X 60

## Colours Available in:

Dark Grey  
Grey  
White  
Cream  
Taupe  
Greige


## Colours



Cream



Dark Grey




Taupe



Greige



Grey



White

# Technical Details

Technical Features	Test Method	Required Values	Average Values
Water Absorption	ISO 10545-3	$\leq 0,5\%$	<b>0,05%</b>
Breaking Strength	ISO 10545/4	$R \geq 35\text{N/mm}^2$	<b>2.200 N 9,5 mm 13.600 N 20 mm</b>
Modulus of rupture	ISO 10545-4	-	<b>50 N/mm<sup>2</sup></b>
Deep Abrasion Resistance	ISO 10545-6	$< 175 \text{ mm}^3$	<b>145 mm<sup>3</sup></b>
Linear Thermal Expansion	ISO 10545-8	$< 9 \times 10^{-6} \text{ C}^{-1}$	<b><math>\alpha</math> <math>\leq</math> <math>7 \times 10^{-6} \text{ }^\circ\text{C}^{-1}</math></b>
Stain Resistance	ISO 10545-14	min, Class 3	<b>5 RESISTANT</b>
Chemical Resistance	ISO 10545-13	Min B	<b>LA-HA RESISTANT</b>
Frost Resistance	ISO 10545-12	-	<b>RESISTANT</b>
Slip Resistance	ANSI A 137.1:2012 BOT 3000 WET DCOF  DIN 51130 R	$\geq 0,42$  water, oil, grease, etc. create slippery conditions. fl or applications with exposure to these conditions require extra caution in product selection	<b>PTV 36+ wet (Sl. 96 - Sl. 55) Grip - Exterior</b>
Length & Width *	ISO 10545-2	$\pm 0.5\%$	<b><math>\pm 0.6\%</math></b>

# Technical Details

Technical Features	Test Method	Required Values	Average Values
Straightness of Sides	ISO 10545-2	-	<b>+0.5%</b>
Rectangularity	ISO 10545-2	-	<b>+0.6%</b>
Warpage	ISO 10545/2	+5%	<b>+0.5%</b>
Thickness	ISO 10545-2	+5%	<b>+5%</b>
Shade Variation	-	-	V2 - Slight Variations
Fire Reaction	EN 14411:2012	-	<b>Class A1 (wall) Class A1fl (floor)</b>
Thermal Conductivity	-	-	<b><math>\lambda = 1,3 \text{ W/m } ^\circ\text{K} /</math> <b>0.7 BTU/ft h °F</b></b>
Recommended minimum joint Interior/Exterior	-	-	<b>2mm 5-6mm circa/approx</b>



Revive Dark Grey

Farba Pearl Brick  
Farba Pearl Linear





Revive Taupe



204 Duggins Lane, Tile Hill, Coventry,  
CV4 9GP  
02475 092 859  
[www.keystoneco.co.uk](http://www.keystoneco.co.uk)

